



S3(n60) High Rigid Medium Wall Hard Jacket Tube for Cable Accessory and Pipeline Industry

Features

- Medium wall cross-linked polyolefin
- Thermal melt adhesive liner
- Halogen free, RoHS compliant
- Operating temperature: -55~105 °C
- Shrink temperature: 135 °C
- Shrink ratio: 3:1

Technical Data

	Property	Test Method	Values
Physical	Tensile strength	ASTM D2671	≥15 MPa
	Breakdown elongation	ASTM D2671	≥400%
Aging (158°C/168hrs)	Tensile strength	ASTM D2671	≥12 MPa
	Breakdown elongation	ASTM D2671	≥350%
	Water absorption (23°C/336hrs)	ASTM D570	≤0.5%
	Density	ASTM D2671	1.05~1.10
	Heat shock (200°C/4hrs)	ASTM D2671	No drop, No flow (outer layer only)
	Hardness(Shore D)	ASTM D2671	60 HD
	Adhesive softening point	ASTM E28	≥85°C
	Adhesive peel strength to XLPE	ASTM D2671	≥110 N/25cm
	Adhesive peel strength to steel	ASTM D2671	≥ 80 N/25cm
	Volume resistivity	ASTM D2671	≥10 ¹⁴ Ω.cm
	Dielectric strength	ASTM D2671	≥15 kV/mm
	Copper corrosion	ASTM D2671	No corrosion

Typical application

- Ideal for insulation and protection for cable accessory and pipeline industry

Ordering

- Standard color : Black
- Standard product is adhesive lined, tubes without adhesive are available on request.
- Standard packaging is 1.22m/pc
- Please provide specification, quantity when ordering

Dimensions

Shrink ratio 3:1

Reference S3(n60)	As supplied(mm) ID min.	After recovered(mm) ID max.	WT nom.	Standard length m
8/2	8	2	2.0	1.22
9/3	9	3	2.0	1.22
12/4	12	4	2.0	1.22
16/5	16	5	2.2	1.22
19/6	19	6	2.5	1.22
22/6	22	6	2.5	1.22
25/8	25	8	2.5	1.22
28/6	28	6	2.5	1.22
33/8	33	8	2.5	1.22
35/12	35	12	2.5	1.22
40/12	40	12	2.5	1.22
45/13	45	13	2.5	1.22
55/16	55	16	2.7	1.22
65/19	65	19	2.8	1.22
75/22	75	22	3.0	1.22
85/25	85	25	3.0	1.22
95/25	95	25	3.0	1.22
115/34	115	34	3.0	1.22
130/36	130	36	3.0	1.22
140/42	140	42	3.0	1.22
160/50	160	50	3.0	1.22
175/58	175	58	3.0	1.22
200/65	200	65	3.0	1.22
230/75	230	75	3.0	1.22
260/85	260	85	3.0	1.22

● ID=Internal Diameter

● WT= Wall Thickness



<http://www.Union-Polymer.com>
 Phone: (513) 899 1618
 Email: Info@Union-Polymer.com